PRODUCT NUMBER AND CONTAINER SIZE

Installation Guidelines

51201 Qt/51101Gal/513015g pail SATIN 51281 Qt/51181Gal/513815g pail

WATER BASED/COVERAGE: One gallon covers approximately 350 SF

MATTE 51271 Qt./51171 Gal.

USE ON:

Unfinished wooden cabinetry and doors, paneling, furniture, and wood railings, as well as some vinyl and other plastic surfaces (always test for compatibility with surface).

LIMITATIONS:

Safecoat sealers are made without formaldehyde preservatives. Do not contaminate. Store in airtight containers. Do not use when indoor temperature is below 55 degrees F. Do not freeze. Thick application, high humidity or conditions other than normal will cause Safecoat to dry and cure more slowly.

SURFACE PREPARATION:

Clean surfaces of dirt, grease, mildew and oil. Apply test patches before undertaking large areas to assure good adhesion and lack of surface contamination. Wood staining should be completed before applying finish coats.

APPLICATION:

Before using, roll the Safecoat Acrylacq container well, then apply as is. Stir product thoroughly every 20 minutes during application.

Apply thinly with a brush, pad or airless sprayer.

DRYING/CURING TIME:

Sandable after 2 - 4 hours, and re-coatable after 4 - 8 hours. The product will continue to cure and become harder over time. Normal conditions include a dry surface, access to fresh air flow, moderate humidity, and temperatures above 55 degrees F.

HEALTH PRECAUTIONS:

As with all coatings and sealers, keep container tightly closed and out of the reach of children. Do not take internally. Keep from freezing. Always use adequate ventilation.

PHYSICAL DATA

Physical Description: Milky dries clear

% Volatile by Volume: 68.31% Solubility in Water: Dilutable % Volatile by Weight: 67.01% VOC Material: 124 g/l VOC Material less H20: 281 g/l

HAP's (Hazardous Air Pollutants) zero


If you are chemically sensitive, always test for personal tolerance.

Test samples available here:

www.thegreendesigncenter.com/product/afm-2ozsamples/

Spraying Guidelines

Safecoat Finish	Acrylacq		Polyureseal BP	
Equipment	HVLP	Airless	HVLP	Airless
Substrate temperature	70-75°	70-75°	70-75°	70-75°
Coating temperature	70-75°	70-75°	70-75°	70-75°
Pot pressure	4	If applicable 15-25 Lbs.		-
Tip	-	9/10		-
Spray pattern	-	FU	LL ———	-
Distance from surface	-	10-	12"	-
Dry time between coats	At ambient temperatures, 30-60 minutes Cooler temperatures or higher humidity will double dry times			





CLEAN-UP:

Clean tools and equipment while they are still wet with a warm soapy water solution.