

# Installation Guidelines

If you are chemically sensitive, always test for personal tolerance.

## USE ON:

orous (unpolished) surfaces such as: marble, limestone, granite, sandstone, slate, brick, concrete (block, tile, precast panels, cast in place)

## DO NOT USE ON:

polished surfaces, countertops, wood, plastic, laminate, vinyl, metal, glass, fabric or any painted surface.

**NOTE:** If you don't see your surface listed here, test with a sample first to be certain that it bonds and covers properly.

## SURFACE PREPARATION:

Clean surfaces of dirt, grease, mildew and oil. New cementitious surfaces should age at least thirty days and have a pH below 10 before coating. Scrub surface with an acid neutralizing cleaner. Triple rinse to assure cleaner is completely removed. Acid-etching may be required, followed by completely neutralizing the surface. Use extreme caution when working with acid and follow label and MSDS precautions. All acid residual must be removed prior to coating. Surface pH should be 7-10 for best results. Test surface porosity and profile by dropping water onto dry surface. If water drops fail to penetrate quickly, surface may need additional attention to create proper surface profile.

## COVERAGE:

One gallon covers approximately 300-400 sf based on surface porosity.

## APPLICATION:

Before using, stir Safecoat MexeSeal well, then apply as is. **APPLY THIN COATS** with a brush, pad or airless sprayer. Use a painter's mask when spraying. Airless sprayers should have a 17/1000 to 21/1000 tip (reversible type is best). Only a 30 mesh high pressure filter should be used. Use a painter's mask when spraying. For full coverage application, overlap preceding application with 1/4 to 1/2 the fan width at a distance of 18" from surface.

**Safecoat paints are made without formaldehyde preservatives and are HAPs free. Do not contaminate. Do not use when indoor temperature is below 55 degrees F. Do not freeze.**

## CLEAN-UP:

Clean tools and equipment while they are still wet with a warm soapy water solution.

## DRYING/CURING TIME:

Re-coatable after 2 hours in normal conditions. Normal conditions include a dry surface, access to fresh air flow, moderate humidity, and temperatures above 55 degrees F

## HEALTH PRECAUTIONS:

As with all coatings and sealers, keep container tightly closed and out of the reach of children. Do not take internally. Keep from freezing. Always use adequate ventilation.

## PHYSICAL DATA

Physical Description:	Low odor, clear
% Volatile by Volume:	81.10%
Solubility in Water:	Dilutable
% Volatile by Weight:	79.40%
VOC Material:	21 g/l
VOC Material less H20:	99 g/l
HAP's (Hazardous Air Pollutants) zero	

**If you are chemically sensitive,  
always test for personal tolerance.**

Test samples available by request.



**LIMITED LIABILITY:** Liability, whether express or implied, is limited solely to replacement of product shown to be defective when applied in accordance with instructions and shall under no circumstances include liability for labor costs or consequential damages. It is the user's responsibility to determine the suitability and safety of the product for its intended use. This limited warranty may not be modified or extended by manufacturer's representatives, distributors, or dealers of AFM products. We particularly recommend that users always test in small inconspicuous areas before application to the entire surface.

**American Formulating and Manufacturing** 3251 Third Ave., San Diego, CA 92103 [www.afmsafecoat.com](http://www.afmsafecoat.com).